


F-WCC CHEMICAL COATED WHITE OPAQUE BOPET FILM

F-WCC is a white opaque polyester film. The film is one side chemical coated and other side corona treated.

KEY FEATURES:

- Excellent opacity & high brightness
- Excellent machinability & handling properties
- Good mechanical & thermal properties
- One side chemical coated and excellent adhesion with inks & adhesive.
- Out side corona treated for improved bond with outer substrate.



APPLICATION:

- Surface Printing jobs & Metallization
- Label application & Blister Packaging
- Other conversion where white backing required like lids

PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUES		
THICKNESS	Internal	Micron	12	23	
THICKNESS		(Gauge)	48	92	
YIELD	Internal	m² / kg	58.27	30.40	
		in² /lb	41022	21401	
SURFACE TENSION (min) (Chemical coated side) (Corona Treated Side)	ASTM D-2578	ASTM D-2578 dyne/cm		60 52	
			52		
COF (max) (One side to the other side)	ASTM D-1894	-	0.50	0.50	
OPACITY (min)	Hunter Lab	%	55	75	
TENSILE STRENGTH AT BREAK (min) $\frac{\text{MD}}{\text{MD}}$ TD	- ASTM D-882	kg/cm²	1700	1600	
			2000	2000	
	ID ASTIVI D-882	(Psi)	24200	22700	
			28500	28500	
ELONGATION AT BREAK (min) MD	ASTM D-882	%	110	115	
			80	80	
LINEAR SHRINKAGE (max) MD (30 Minute at 150°C) TD	- ASTM D-1204	%	2.5		
			0.8		
W.V.T.R. (38° C & 90% RH) (typical)	ASTM F-1249	gm/m²/day	45	25	
vv.v.i.iv. (30° C & 30% KH) (typical)		(gm/100 in²/day)	2.9	1.6	
OTR (23°C & 0% RH) (typical)	ASTM D-3985	cc/m²/day	160	75	
OTT (25 C & On IT I) (typical)	1.52 5565	(cc/100 in²/day)	10.3	4.8	

STORAGE & HANDLING

SELEXIBLE need to be stored in a warehouse below 35°C (95°F) and should not be exposed to direct sunlight, bright light sources or high humidity. If the material is stored in the recommended conditions, SELEXIBLE is suitable for use within 270 days from date of shipment.

FOOD CONTACT

SELEXIBLE complies with EU and FDA regulations on plastic materials used for food grade application. Specific document and SDS are available on request.

DISCLAIMER

It is the responsibility of our customers to determine that their use of our products is safe, lawful, and technically suitable in their intended applications. The technical data sheets are provided for discussion purposes only. The customer may not rely on the data provided for any manufacturing purpose. The values provided in the technical data sheet represent typical values based on the best of our knowledge as of the date when the data was compiled. The data is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability/compatibility in all respects. Selexible provides no warranty and accepts no liabil ity for any loss or fitness of the product for any specific purpose based on the information contained in the technical data sheets. Selexible reserves the right to change the technical data sheet at any time without prior notice.

Selexible

Manufacturing Facilities at No. 16 Fengxiang Rd, Wujin District, Changzhou City, Jiangsu, China sale@selexible.cn www.selexibleplastic.com