

# F-MSU


## SPECIAL CHEMICAL COATED SUPER MATT FILM

F-MSU is a Super Matt effect BOPET film. The Film is one side Special Chemical coated and other side Untreated or Corona treated.

### KEY FEATURES:

- Super Matt effect
- One side chemical coating provide excellent adhesion with inks & adhesives
- Excellent machinability & handling properties
- Good stiffness

### FILM STRUCTURE



### APPLICATION:

- Thermal lamination
- Label application
- Conversion application
- Board lamination

PROPERTIES		TEST METHOD	UNIT	TYPICAL VALUES		
THICKNESS		Internal	Micron	12	19	23
			(Gauge)	48	76	92
YIELD		Internal	m² / kg	59.52	37.59	31.05
			in² /lb	41934	26483	21876
SURFACE TENSION (min) # (Special Chemical Coated Side)		ASTM D-2578	dyne/cm	48		
COF (max) (One side to the other side)		ASTM D-1894	-	0.45	0.40	0.40
HAZE (min)		ASTM D-1003	%	70	75	85
GLOSS AT 45° angle		ASTM D-2457	-	28	26	25
TENSILE STRENGTH AT BREAK (min)	MD	ASTM D-882	kg/cm²	1500	1500	1400
	TD			1900	1900	1900
	MD		(Psi)	21400	21400	19900
	TD			27000	27000	27000
ELONGATION AT BREAK (min)	MD	ASTM D-882	%	110	120	130
	TD			75	80	85
LINEAR SHRINKAGE (max) (30 Minute at 150°C)	MD	ASTM D-1204	%	3.0		
	TD			1.0		
W.V.T.R. (38° C & 90% RH) (typical)		ASTM F-1249	gm/m²/day	45	35	30
			(gm/100 in²/day)	2.9	2.3	2.0
OTR (23° C & 0% RH) (typical)		ASTM D-3985	cc/m²/day	130	90	80
			(cc/100 in²/day)	8.5	5.8	5.2

# The inherent surface tension of the untreated side of any Pet film is minimum 42 dyne/cm

### STORAGE & HANDLING

SELEXIBLE need to be stored in a warehouse below 35°C (95° F) and should not be exposed to direct sunlight, bright light sources or high humidity. If the material is stored in the recommended conditions, SELEXIBLE is suitable for use within 270 days from date of shipment.

### FOOD CONTACT

SELEXIBLE complies with EU and FDA regulations on plastic materials used for food grade application. Specific document and SDS are available on request.

### DISCLAIMER

It is the responsibility of our customers to determine that their use of our products is safe, lawful, and technically suitable in their intended applications. The technical data sheets are provided for discussion purposes only. The customer may not rely on the data provided for any manufacturing purpose. The values provided in the technical data sheet represent typical values based on the best of our knowledge as of the date when the data was compiled. The data is offered solely to provide possible suggestions for your own experimentation and not as a guarantee for the material supplied. The user is solely responsible for the end use of the product and needs to perform their own tests to confirm the product suitability/compatibility in all respects. Selexible provides no warranty and accepts no liability for any loss or fitness of the product for any specific purpose based on the information contained in the technical data sheets. Selexible reserves the right to change the technical data sheet at any time without prior notice.

## Selexible

Manufacturing Facilities at No. 16  
 Fengxiang Rd, Wujin District,  
 Changzhou City, Jiangsu, China  
 ✉ sale@selexible.cn  
 www.selexibleplastic.com